

Medium Oil Alkyd Resin

SALES CODE	Type of Oil or Fatty acid	Oil%	Color Gardner	Viscosity @25°C	Acid Value	Solid%	Solvent	Application
EPAL-6100 55% WS	Soya	46%	5 max	Z6-Z7 @55%	15 max	53-57	White Spirit	Air dry metal primer and finishes, Enamel undercoat, car repair finishes
EPAL-6101 55%WS	Soya	45%	5 max	Z4-Z5 @55%	15 max	53-57	White Spirit	Car repair refinish, Machinery and drum coatings
EPAL-6102 60%WS	Soya	49%	5 max	Z3-Z4 @ 55%	15 max	58-62	White Spirit	Air dry metal primer and finishes, Enamel undercoat, Economical stoving enamel temp.140 to 160°C, Interior and exterior decorative paints
EPAL-6103 60% XL	Soya	43%	5 max	V-X @ 60%	15 max	58-62	Xylene	Air dry metal primer and finishes, car repair finishes, Machinery and drum coatings
EPAL-6104 60%XL	Soya	42%	5 max	V-X @ 50%	15 max	68-72	Xylene	Air dry metal primer and finishes, car repair finishes, Machinery and drum coatings, High quality industrial enamel
EPAL-6105 60%XL	Soya	45%	5 max	Z2-Z3	12 max	58-62	Xylene	Car repair refinish, Machinery and drum coatings